

SMART+ Wheel Paint

Mipa Paints Ltd
Applied House
Fullood Road
Havant
Hants
PO9 5AX

Tel: 02392 474234 Fax: 03300 579 559 www.monofil.co.uk

1. Introduction

Silver wheel is a premium quality, fast drying acrylic paints specially designed for application to automotive wheels, particularly when used in conjunction with SMART+ PRIMERS. Ideal for use on passenger cars, commercial vehicles as well as many other industries.

2. Where to use

- On all types of automotive wheels including steel, alloy, and plastic trims.

3. Where not to use

- On surfaces treated with primers of unknown composition, without first ascertaining suitability of use.

4. Benefits

- Fast Drying
- Enhanced covering power
- Excellent durability
- Non-yellowing. excellent resistance to sunlight and colour fade
- Excellent adhesion to primed surfaces
- Professional standard application from the adjustable fan spray nozzle

5. Physical properties [Acrylic finish bases except where stated].

Appearance	Coloured liquids with characteristic paint solvent odours.
pH	Not applicable
Specific Gravity	0.94 – 1.02
Viscosity	Up to 1,500cPs
Non-Volatiles % m/m	35 - 55
Active Content % m/m, as supplied	10 - 20
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	A solvent based solution of an acrylic resin containing a range of pigments, extenders, plasticizers, thixotropes and ultraviolet light absorbers dispersed in a butane/propane/isobutane-based propellant.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 80°C
Application Temperatures	15 - 25°C

6. Application Details

Prepare the primed area to be treated, ensuring freedom from dust, grime, greases, oils etc, with a solvent wipe using white spirit, thinners or a proprietary panel wipe and allow to dry.

**SMART+
Wheel Paint**

Mipa Paints Ltd
Applied House
Fulford Road
Havant
Hants
PO9 5AX

Tel: 02392 474234 Fax: 03300 579 559 www.monofil.co.uk

If necessary, the surface may be flattened by abrading the surface lightly, using 1200 grade wet and dry abrasive paper, and solvent treated as described above to remove any dust.

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use. Apply sparingly from a distance of 20 – 25cm. Apply as many coats as necessary to achieve total and even coverage, leaving at least 15 minutes between each application. Allow at least 24 hours to harden. On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

Not suitable for over-lacquering.

7. Availability

500ml aerosols

MIPA Paints January 2020.