

**SMART+
ACRYLIC PRIMERS
Grey, Red and White**

Mipa Paints Ltd
Applied House
Fulford Road
Havant
Hants
PO9 5AX

Tel: 02392 474234 Fax: 03300 579 559 www.monofil.co.uk

1. Introduction

A range of fast drying acrylic based primers designed to provide a durable finish. Ideal for use on passenger cars, commercial vehicles as well as many other industries.

2. Where to use

- On all types of automotive body panels for rectification and repair work.

3. Where not to use

- On surfaces treated with primers of unknown composition, without first ascertaining suitability of use.

4. Benefits

- Fast Drying
- Enhanced covering power
- Excellent adhesion to metals and rigid plastics
- Professional standard application from the adjustable fan spray nozzle

5. Physical properties [Acrylic Primer bases except where stated].

Appearance	Coloured liquids with characteristic paint solvent odours.
pH	Not applicable
Specific Gravity	1.155 – 1.225
Viscosity	500 – 1,500cPs
Non-Volatiles % m/m	50 - 60
Active Content % m/m, as supplied	15 - 25
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	A solvent based solution of an acrylic resin containing a range of pigments, extenders and thixotropes dispersed in a butane/propane/isobutane-based propellant.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 80°C
Application Temperatures	15 - 25°C

6. Application Details

Prepare the area to be treated, ensuring freedom from dust, grime, traffic film, greases, oils etc. Following preparation lightly abrade surface, remove any dust with a solvent wipe, white spirit, thinners or a proprietary panel wipe and allowed to dry. Mask area to prevent overspray.

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.

TECHNICAL DATA SHEET

**SMART+
ACRYLIC PRIMERS
Grey, Red and White**

Mipa Paints Ltd
Applied House
Fulford Road
Havant
Hants
PO9 5AX

Tel: 02392 474234 Fax: 03300 579 559 www.monofil.co.uk

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.

Apply several light coats from a distance of 20 – 25cm. Apply as many coats as necessary to achieve total and even coverage, leaving at least 15 minutes between each application.

Sandable after approx. 2 hours. Allow at least 24 hours to harden.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

.

7. Availability

500ml aerosols

MIPA Paints January 2020.